

| Property                          | Test Method Standard           | Standard Review                              |
|-----------------------------------|--------------------------------|----------------------------------------------|
| Use of class                      | EN ISO 10874                   | Class 23,32                                  |
| Formaldehyde emission             | EN 717-1                       | E1                                           |
| Reaction to fire                  | EN 13501-1                     | Bfl-s1                                       |
| Slip resistance                   | EN 13893                       | Class DS                                     |
| Slip resistance                   | DIN EN 16165                   | R9/R10                                       |
| Wear resistance                   | ISO 24338 PROCEDURE A          | ≥ 4000 cycles                                |
| Micro-scratch resistance          | EN 16094                       | ≤ MSR-A3                                     |
| Impact resistance (big ball)      | EN 13329                       | ≥ 1200mm                                     |
| Effect of furniture leg           | EN ISO 16581                   | No visible damage                            |
| Castor chair resistance           | EN ISO 4918                    | 25000 cycles                                 |
| Resistance to staining            | EN 438-2                       | Groups 1 and 2: grade<br>5 Group 3: grade 4  |
| Locking strength[kN/m]            | ISO 24334                      | Long side ≥ 1,0kN/m;<br>Short side ≥ 1,5kN/m |
| Light stability                   | EN ISO 105-B02                 | ≥ 6                                          |
| Antistatic resistance             | EN 1815                        | < 2kV                                        |
| Thermal conductivity & Resistance | EN 12664                       | 0.112 W/(m·K) & 0.085 (m².K)/W               |
| Dimensional stability             | EN ISO 23999                   | ≤ 1mm                                        |
| Curling after exposure to heat    | EN ISO 23999                   | ≤ 0.1mm                                      |
| Residual Indentation              | ISO 24343-1                    | 21 db(with underlayer)                       |
| Sound Insulation                  | ISO 10140-3 ISO 717-2          | A+                                           |
| VOC emissions                     | ISO 16000 PARTS -3, -6, -9, 11 | Certified                                    |
| CE                                |                                | Certified                                    |
| UKCA                              |                                | Class 23,32                                  |
| EPD                               |                                | Certified                                    |
| Floorscore                        |                                | Certified                                    |
| Indoor Air Comfort Gold           |                                | Certified                                    |
| Utilization                       |                                | Recyclable                                   |